



NOVATTANE 2100

2-component PU structure adhesive

PRODUCT DESCRIPTION

The NOVATTANE 2100 is a structure adhesive with very high mechanical performances for structure bonding a large variety of substrates: mainly composites (GRP, epoxy, etc.) but also thermoplastics, metal, wood, concrete, fibrocement, etc.

- Thixotropic (it does not sag).
- Very fast cure at room temperature.
- Good resistance to temperature, humidity and weathering.
- Very high mechanical resistance.

PRODUCT CHARACTERISTICS

Chemical Class	Polyurethane
Appearance(mixed)	Gray
% Solids by Volume	100
Shelf life, months	12

Shear strength on Stainless steel, ASTM D1002, MPa	12.97
Shear strength on Galvanized steel, ASTM D1002, MPa	13.92
Shear strength on Al alloy 3003, ASTM D1002, MPa	10.03
Shear strength on Al alloy 6061, ASTM D1002, MPa	11.03
Shear strength on Al, ASTM D1002, MPa	10.01
Shear strength on PET film, ASTM D1002, MPa	1.51

TYPICAL PROPERTIES OF UNCURED MATERIALS

Adhesive Part

Appearance	Milky
Specific gravity@25 °C	1.23
Viscosity@25 °C, Brookfield	
Spindle #92, 20 rpm, cP	60000~90000
Thixotropic Index, 2rpm/20rpm	3.3

Activator Part

Appearance	Black
Specific gravity@25 °C	1.87
Viscosity@25 °C, Brookfield	
Spindle #92, 20 rpm, cP	60000~90000
Thixotropic Index, 2rpm/20rpm	2.3

Mixed

Mix Ratio, by vol, Resin to Hardener	100 : 100
Mix Ratio, by wt, Resin to Hardener	100 : 152
Working time @ 25°C, mins	3~4
Fixture time @ 25°C, hrs	0.5
Full cure @ 25°C, days	7

TYPICAL PROPERTIES OF CURED MATERIALS

Fully Cured Product (7 days @ 25 °C)

Density(cured), g/cm ³	1.55
Coefficient of thermal conductivity, ASTM E1461, W/(m·K)	0.5
Dielectric strength ASTM D149, kV/mm	13
Shore D hardness, ASTM D2240	70
Tensile strength, ASTM D638, MPa	30
E modulus, ASTM D638, MPa	2650
Elongation at break, ASTM D638	5~10%

TYPICAL CURING PROCESS

7days @ 25 °C . For ultimate chemical and thermal resistance, allow parts to cure overnight at room temperature, then follow with 2hrs of 80 °C exposure.

SURFACE PREPARATION

The surfaces must be dry, degreased and dust free. The treatment may be varied according the substrate (paper sanding, degreasing, Corona treatment, etc.): consult with the technical service.

APPLICATION INSTRUCTIONS

1. Apply mixed PU directly to one surface in an even film or as a bead.
2. Assemble with mating part within recommended working time.
3. Apply firm pressure between mating parts to minimize any gap and ensure good contact (a small fillet should flow out the edges to display adequate gap fill).

PRECAUTIONS

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

STORAGE



Store the unopened product in a cool, dry, well ventilated location away from sources of heat. Optimal storage temperatures should range between **10 °C (50 °F) and 30 °C (86 °F)**. Product removed from the containers during use should not be returned to original containers in order to avoid potential contamination.

CONVERSIONS

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

WARRANTY

ITW will replace any material found to be defective. Because the storage, handling and application of this material are beyond our control, we can accept no liability for the results

obtained.

NOTE

The following supersedes any provision in your company's forms, letters and papers. ITW makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, and INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW sole opinion, to justify such refund.

For technical assistance, please call: 86-021-54265119

FOR INDUSTRIAL USE ONLY